

(11) (21) **PI 9302312-0 A** [illegible]

(22) Delivery Date: 06/30/93

FEDERAL REPUBLIC OF BRAZIL
Ministry of Industry, Commerce and Tourism
National Institute of Industrial Property

(43) Publication Date: 02/07/95 (BR) (262)

(54) Title: The Biopolymer Extraction Process

(71) Applicant(s): Cooperativa dos Produtores de Cana, Açúcar e Alcool do Estado de São Paulo Ltda (*Sugar Cane, Sugar, and Alcohol Production Cooperative of the State of São Paulo, LTD*)
COPERSUC (BR/SP) Instituto de Pesquisas Tecnológicas do Estado de São Paulo S/A-IPT (BR/SP) (*Institute of Technological Research of the State of São Paulo*)

(72) Inventor(s): Silas Derenzo, Rosa Mitiko Salto Matsubara, Gracinda Martins Correia Garofalo, Alice Maria de Melo Ribeiro, Celso Leila Bueno Nuno, Paulo Eduardo Moretto, Carlos Eduardo Vaz Rossell

(74) Patent Agent: Fernando Garcia Gnoochi

(57) Summary: Patent for "THE BIOPOLYMER EXTRACTION PROCESS" the cells containing biopolymer are subjected to a single adequate solvent and polymer insolubility in the solvent is achieved without an insoluble agent.


THE BRITISH
LIBRARY

May 2, 1995
SCIENCE
REFERENCE AND
INFORMATION
SERVICE

Descriptive Report of the "BIOPOLYMERS EXTRACTION PROCESS" Invention

INTRODUCTION

There are various types of soil bacteria that accrue reserve materials under unbalanced growth conditions. In some specific types, the materials are the polyhydroxyalcanoates (PHA), which are aliphatic polyesters, are insoluble in water, and repeat the following structure:



Where,

R, belongs to the n-alkyl group and contains a variable length

(R= methyl, hydroxybutirate (HB))

(R= ethyl, hydroxyvalerate (HV))

(R= propyl, hydroxycapranoate (HC))

(R= buthyl, hydroxyheptanoate (HP))

(R= penthyl, hydroxyoctanate (HO))

The PHA microbial polymer can reach between 10% to 90% of the bacteria's dry weight. This is a thermoplastic polymer that contains characteristics analogous to those found in conventional plastic resins. In addition, this polymer is biodegradable.

The cells that contain a high degree of the biopolymer